PRODUCT SPEC SHEET



Teflex Woven

- Teflex Woven is a pure woven PTFE.
- Teflex Woven is capable of running at high temperatures.
- Continuously operating at 260°C / 500°F with short term surges at 280°C / 536°F.
- Can be used on products across the full pH scale, i.e. either caustic or acid products will not effect Teflex Woven.





PHYSICAL PROPERTIES:

| Fibre | PTFE |
|---|---|
| Colour | Natural (dark brown) |
| Construction/finish | Basket weave |
| Weight | 678 g/m ² |
| | 20 oz/yd ² |
| Thickness (mm) | 0.5mm / ½4″ |
| Max. Operating Temp | 260°C/500°F |
| Max. Surge Temp | 280°C/536°F |
| Low Temp Flexibility | Good |
| Surface Resistance (Ohms) | Insulative |
| Minimum Tensile Strength measured as a force over a 25mm wide Ravel Strip (Test Standard: ASTM D5035) | Fabric Warp 90) _{kgf/25mm} Weft 100) |
| Ultimate Elongation (%) (Test Standard: ASTM D5035) | 55 |
| Air Permeability: (cm³/cm² sec@125Pa) (ft³/ft²/min@0.5″ wg) | 0.3 0.5 |
| AVAILABLE SIZES: (in | 50mm / 2" increments) |
| Diameter (also available in 125mm/5") | Ø100mm, 150mm to 1,650mm (4", 5" to 65") |
| Length | 80mm , 100mm to 1,500mm (3", 4" to 59 ‰") |

NB: Some size restrictions apply for TR versions, larger diameters and connectors with rings.

COMPLIANCE:

Atex Compliant: IBExU tested. Can be used in certain dust explosion hazardous areas (restrictions apply). PTFE is compliant with FDA 21 CFR 177.1550, 178.3297.

ARL PRODUCTS, LLC | EMAIL: info@flexiblefittings.com | WEB: flexiblefittings.com | PH: 281-203-8577